



SPECIFICATION

CHLOROBUTYL RUBBER RECLAIM

Parameters	Unit	Grades
		RC55
CHEMICAL PROPERTIES		
ACETONE - EXTRACT	%	13 ± 3
ASH CONTENT	%	4 ± 2
CARBON BLACK	%	Min 27
RUBBER HYDRO CARBON	%	Min 50
VOLATILE MATTER	%	<1
PHYSICAL PROPERTIES		
Physical Apperance		Black Slab
SPECIFIC GRAVITY		Max 1.15
TENSILE STRENGTH	KG/ Sq. Cm	Min 55
ELONGATION	%	Min 450
HARDNESS SHORE "A"		45 ± 5
MOONEY VISCOSITY ML (1+4) @ 100 °C		40-60