



SPECIFICATION

NATURAL RUBBER RECLAIM

Parameters	Unit	Grades
		NR
CHEMICAL PROPERTIES		
ACETONE - EXTRACT	%	12 ± 4
ASH CONTENT	%	Max 28
CARBON BLACK	%	17 ± 7
RUBBER HYDRO CARBON	%	Min 40
VOLATILE MATTER	%	<1
PHYSICAL PROPERTIES		
Physical Apperance		Black Slab
SPECIFIC GRAVITY		1.25 ± 0.05
TENSILE STRENGTH	KG/ Sq. Cm	Min 30
ELONGATION	%	Min 225
HARDNESS SHORE "A"		60 ± 5
MOONEY VISCOSITY ML (1+4) @ 100 °C		20-50