



## SPECIFICATION

### **CBS(CZ) N-Cyclohexy-2-benzothiazole sulfonamide**

NAME OF INDEX	FIRST GRADE
Appearance	grayish-white or light yellow powder
Melting point, ° C, min	TM 98.0
Heating loss, %, max	0.30
Ash content, %, max	0.30
Residue(150µm),%,max	0.05

#### APPLICATION

CBS(CZ) is an accelerator with high activity and greatly delayed action, has high antiscorching quality, processing safety and short cure time. Its activity can be reinforced by thiuram and dithiocarbamate type alkaline accelerators. Mainly used in manufacture of tires, rubber shoes, cable and other technical rubber goods.

#### PACKAGE

In knitted bag lined with plastic bag or kraft paper bag. 25kgs/bag or at byer's request.