

SPECIFICATION MBS (NOBS) N-Oxydiethylent-2benzothiazole sulfonamide

NAME OF INDEX	FIRST GRADE
Appearance	Light yellow or orange colour pellet
Melting point, ° C, min	80.0
Heating loss, %, max	0.50
Ash content, %, max	0.30

APPLICATION

NOBS is a vulcanization acceleration with delayed action, short cure time, has high anti-scorching quality and processing safety. It is suitable for NR and SR. Mainly used in manufacture of tires, rubber tubes, rubber shoes, rubberizer tape and other technical rubber goods.

PACKAGE

In knitted bag lined with plastic bag or kraft paper bag. 25kgs/bag or at buyer's request.

