



## SPECIFICATION

### MBT (M) 2-Mercaptobenzothiazole

NAME OF INDEX	FIRST GRADE
Appearance	grayish-white or light yellow powder
Melting point, ° C, min	171.0
Heating loss, %, max	0.40
Ash content, %, max	0.30
Residue(150µm),%,max	0.10

#### APPLICATION

Accelerator M is a hemi-ultra accelerator of NR and SR, has wide range of vulcanization. It can be applied alone and together with dithiocarbamates, thiuram type, guanidines and other alkaline accelerators. Mainly used in manufacture of rubber tires, belts, rubber shoes and other technical rubber goods.

#### PACKAGE

In knitted bag lined with plastic bag or kraft paper bag. 25kgs/bag or at buyer's request.