



SPECIFICATION

ZDEC (EZ) Zinc Diethyl Dithiocarbamate

NAME OF INDEX	FIRST GRADE
Appearance	White or light yellow powders
Melting point, ° C, min	™ 174.0
Heating loss, %, max	0.40
Ash content, %, max	17.0-19.0
Residue(150µm),%,max	0.10

APPLICATION

A fast curing accelerator for natural, synthetic rubber and latex, especially suitable for butyl rubber, EPDM rubber and latex. Non-toxic, inodorous, it can be used as white or colour and transparent rubber manufactures.

PACKAGE

In knitted bag lined with plastic bag or kraft paper bag. 25kgs/bag or at buyer's request.