



SPECIFICATION

CTP (PVI) N-(cylhexyl thio) phthalimide

| NAME OF INDEX | FIRST GRADE |
|--------------------------------------|--|
| Appearance | White or light yellow powdered crystal |
| Melting point, ° C, min | 89-94 |
| Available composition content,%max | 96 |
| Heating loss, % | 0.5 |
| Ash Content, % ,max | 0.1 |
| Insoluble matter in toluene, %, max, | 0.5 |
| Identification IR | Identical to standard |

APPLICATION

The product may be used in natural rubber and synthetic rubber. It may protect effectively the rubber material from scorching during Processing, So that to make it possible for extruder and calendar to be running at a high temperature and high speed and improve the production capacity of vulcanizer. The product also can improve the storage stabilization of the rubber material, protect natural vulcanization during storage. It has reclamation function for rubber material, which bearing high heating or with dangers of scorching.

PACKAGE

In knitted bag lined with plastic bag or kraft paper bag. 25kgs/bag or at buyer's request.