



## SPECIFICATION

### CHLOROBUTYL RUBBER (CIIR)

HS CODE - 40021190 | CAS NO - 9003-55-8

Property	Value
Mooney Viscosity, ML 1+8 (125 °C)	34-44
Chlorine mass content, %	1.15-1.35
Ash mass content, % max	0.5
Irganox 1010 antioxidant mass content, %	0.05
Loss of mass at drying, % max	0.5
Modules at 300% elongation, Mpa, min.	4
Tensile strength, Mpa, min.	12
Ultimate elongation, % min.	400

#### APPLICATION

It is used in production of tyres rubber-technical articles.

#### PACKAGE

30+1 kg bales. Polyethylene file, wooden and metal pallet boxes.