



GANPATI EXIM™
Pursuing Excellence

SPECIFICATION

TSR 3L

Standard Technical Data Sheet for TSR 3L
Raw Material - Field Latex

Properties	Unit	*Limit
Dirt Content - Max	% Wt	0.03
Ash Content - Max	% Wt	0.50
Volatile Matter - Max	% Wt	0.80
Nitrogen Content - Max	% Wt	0.60
Initial Wallace Plasticity (PO) - Min		35
Plasticity Retention Index (PRI) - Min		60
Lovibond - Max		6

*These figures represent standard limits. Actual parameters can vary between manufacturers and regions.

Packing :

35 kg/Bale

Loose bales, Shrink Wrapped Wooden/Disposable Plastic Pallet, Metal box.